

## TECHNICAL DATA SHEET

## 73005T

**73005 T** is a rotomolding grade LLDPE produced by the Spherilene Technology with controlled morphology, excellent balance of processability & mechanical properties

**73005 T** is ideally suited for Tanks and Containers for domestic and Industrial water storage, sanitation and agriculture.

Property	Test Method	Unit	Value
Melt Flow Index (2.16Kg, 190°C)	ASTM D 1238	g/10 min	5.0
Density (23°C)	ASTM D 1505	g/cm <sup>3</sup>	0.934
<b>Physical Property</b>			
Tensile Strength at Yield	ASTM D 638	MPa	17
Elongation at Break	(50 mm/min)	%	>500
Flexural Modulus	ASTM D 790A	MPa	500
Notched Izod Impact Strength (23°C)	ASTM D 256A	J/m	450
Heat Deflection Temperature (0.455 MPa)	ASTM D 648	°C	74
Vicat Softening Point (10N)	ASTM D 1525	°C	115

### Suggested Processing Conditions

Oven Temperature	°C	240 – 280
------------------	----	-----------

\* Halene L is the registered trademark of Linear Low Density Polyethylene of HPL

Mechanical properties are on injection molded specimens

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance certificates and MSDS are available on request.  
Visit us at [www.haldiapetrochemicals.com](http://www.haldiapetrochemicals.com)