

TECHNICAL DATA SHEET

M5025L

M5025L is an Injection Molding Grade HDPE produced by Spherilene Technology.

This resin is particularly recommended for general-purpose Injection Molded items and Masterbatch application.

M5025L combines excellent processability with good mechanical properties.

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg at 190 °C)	ASTM D 1238	g/10 min	30.0
Density (23 °C)	ASTM D 1505	g/cm ³	0.950
Physical Property			
Tensile Strength at Yield	ASTM D 638	MPa	20
Elongation at Break	(50 mm/min)	%	250
Notched Izod Impact Strength (23 °C)	ASTM D 256A	J/m	28
Flexural Modulus	ASTM D 790A	MPa	800
Spiral Flow Length @ 235 °C	HPL Method	mm.	730
Hardness	ASTM D2240	Shore D	62
Vicat Softening Point(10N)	ASTM D 1525	°C	125
Heat Deflection Temperature (0.455 MPa)	ASTM D 648	°C	77
DSC Melting Temperature	ASTM D 3418	°C	132

Suggested Processing Conditions

Barrel Temperature	°C	180 – 235
Nozzle Temperature	°C	235

* Halene H is the registered trademark of High Density Polyethylene of HPL

Mechanical properties are on injection molded specimens

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance certificates and MSDS are available on request.
Visit us at www.haldiapetrochemicals.com