

## TECHNICAL DATA SHEET

### M106

Polypropylene Homopolymer

### Characteristics

**M106** is a **Polypropylene Homopolymer**, produced by the latest generation **Spheripol II Technology**. This homopolymer is primarily suitable for **Injection Molding Process**.

**M106** combines **easy processability with high strength**.

### Application

- **General Purpose Injection Molding**

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg & 230 <sup>0</sup> C)	ASTM D 1238	g/10 min	6
Density at 23°C	ASTM D 1505	g/cm <sup>3</sup>	0.90
Tensile Strength at Yield (50 mm/min)	ASTM D 638 (Type I - with Extensometer)	MPa	30
Tensile Elongation at Yield (50 mm/min)		%	7
Flexural Modulus	ASTM D 790A	MPa	1300
Notched Izod Impact Strength (23°C)	ASTM D 256A	J/m	35
Vicat Softening Point (10N)	ASTM D 1525	°C	153
Heat Deflection Temperature (0.455 MPa)	ASTM D 648	°C	93

### Typical Processing Temperature

Barrel Temperature	°C	180 - 260
Mold Temperature	°C	30 - 40

*Mechanical properties are tested on Injection Molded Test Specimens prepared as per ASTM D 4101*

*The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.*

Compliance Certificates & MSDS are available on request.

Visit us at [www.haldia Petrochemicals.com](http://www.haldia Petrochemicals.com)