

TECHNICAL DATA SHEET

M311T

Polypropylene Impact Copolymer

Characteristics

M311T is a **Heterophasic Polypropylene Impact Copolymer (PPiCP)**, produced by the latest generation **Spheripol II Technology**. This PPiCP is primarily suitable for **Injection Molding** process. M311T combines excellent **processability with high flow, low cycle time, good Impact – Stiffness balance with high Toughness and good Gloss**.

Application

- Automotive Components
- Compounding
- Luggage
- Industrial Components

Property	Test Method	Unit	Value
Melt Flow Index (2.16 kg & 230 ^o C)	ASTM D 1238	g/10 min	10
Density at 23°C	ASTM D 1505	g/cm ³	0.90
Tensile Strength at Yield (50 mm/min)	ASTM D 638	MPa	21
Tensile Elongation at Yield (50 mm/min)	(Type I - with Extensometer)	%	7
Flexural Modulus	ASTM D 790A	MPa	900
Notched Izod Impact Strength (23°C)	ASTM D 256A	J/m	500
Vicat Softening Point (10N)	ASTM D 1525	°C	142
Heat Deflection Temperature (0.455 MPa)	ASTM D 648	°C	85

Typical Processing Temperature

Barrel Temperature	°C	160 - 250
Mold Temperature	°C	30 – 40

Mechanical properties are tested on Injection Molded Test Specimens prepared as per ASTM D 4101

The information & data presented herein are typical values and should not be construed as specification. No warranty or guarantee expressed or implied is made regarding performance. The information & data are subject to change without prior intimation based on research & development work undertaken by the company.

Compliance Certificates & MSDS are available on request.

Visit us at www.haldia Petrochemicals.com